



ALP OVERSEAS MATERIAL & PRODUCT TESTING LAB.

KHASRA NO. 744, 745, 748/2463, 728, 698/2236 AND 683,
VILLAGE GUGALKOTA, NEEMRANA, ALWAR,
RAJASTHAN, INDIA

Test Report No.: 2506024082

Report Issue Date: 19-06-2025


Test Report

CUSTOMER NAME & ADDRESS:

ALP AEROFLEX INDIA PVT. LTD.
ALP POLYMER PARK, VILL. GUAGALKOTA
NEEMRANA, ALWAR-301706 RAJASTHAN

CONTACT PERSON NAME	MR. SANIL KUMAR
SAMPLE NAME / DESCRIPTION	ALP ACRITE SHEET (PMMA)/LAMINATES
SAMPLE RECEIVED DATE	10-06-2025
SAMPLE CONDITION (PHYSICAL)	OK
TESTING PERIOD	16-06-2025 TO 18-06-2025
TEST REQUESTED	TRANSPARENCY

SAMPLE PHOTOGRAPH



INSTRUMENT USED

INSTRUMENT NAME	INSTRUMENT MAKE	INSTRUMENT ID.	CALIBRATION DATE	CALIBRATION DUE DATE
HAZE METER	CHN Spec	ALPO/R&D/66	29-08-2024	28-08-2025

Laboratory Environmental Condition

Temperature (°C)	23.5
Relative Humidity (%)	53

This document is provided by the Company upon request based on the Test request form. Any individual possessing this document is advised that the information it contains represents the Company's findings solely at the time of its involvement and within the confines of the Client's instructions, if applicable. The Company's responsibility is completely towards its Client and are committed to practice confidentiality. Any unauthorized modification, forgery, or alteration of any kind of the content or appearance of this document is illegal, and individuals responsible may face legal prosecution to the maximum extent permissible by law. Unless explicitly stated otherwise, the results presented in this test report pertain exclusively to the tested sample(s), and said sample(s) will be retained for a duration of 15 days & in case of failure 30 days. Reproduction of this document, in whole or in part, is prohibited without prior approval from the Company. And if in case of reproduction of this document from the company the past report will be invalid and to be disposed both by the company and the client. *GENERAL TERMS AND CONDITION



ALP OVERSEAS MATERIAL & PRODUCT TESTING LAB.

KHASRA NO. 744, 745, 748/2463, 728, 698/2236 AND 683,
VILLAGE GUGALKOTA, NEEMRANA, ALWAR,
RAJASTHAN, INDIA

Test Report No.: 2506024082

Report Issue Date: 19-06-2025

Test Report

Test Name : Transparency

Test Method : ASTM D1003:21

Test Condition :

1) Preconditioning : 40hrs. at Temp. $23 \pm 2^{\circ}\text{C}$ & RH $50 \pm 10\%$

2) Sample Size : 60mm X 60mm X 2mm

Observation :

S.N.	Transparency (%)
1	92.91
2	92.62
3	92.57
Average	92.70

Statement of conformity : NA

- Note:**
- 1- The Results relate only to the items tested.
 - 2- This Report cannot be reproduced without the written approval of the laboratory.
 - 3- Lab do not draw the sample(s) from the customer.

***** End of Report*****

Reviewed By:
Vikash Singh
(Technical Manager)

Authorized Signatory:
Bhojraj Padhan
(Head of Laboratory)